

1-Component STP Wood Flooring Adhesive

UZIN MK 200 T

Hard elastic adhesive for tongue and groove wood flooring

MAIN APPLICATION FIELD:

- ▶ engineered wood flooring

SUITABLE ON / FOR:

- ▶ calcium sulphate or cementitious screeds, concrete
- ▶ new P4 - P7 or OSB 2 - OSB 4 boards, screwed
- ▶ precast screeds, screed boards
- ▶ smoothing compounds suitable for wood flooring
- ▶ UZIN insulating and installation underlays suitable for wood flooring
- ▶ warm water underfloor heating systems



PRODUCT BENEFITS/FEATURES:

UZIN MK 200 T is a thixotropic, moisture-curing adhesive with a long working time. Excellent filling capacity and adhesion combined with a long open time helps with the reliable installation of large wood flooring, even at high temperatures and/or humidity. The tube version of UZIN MK 200 is designed for applications with the adhesive dispenser UZIN ATD 100. For interior use.

- ▶ great adhesion
- ▶ good ridge formation
- ▶ long working time
- ▶ for applications with UZIN ATD 100
- ▶ hard elastic adhesive according to ISO 17 178
- ▶ adhesive residues on wood flooring can be removed



TECHNICAL DATA:

Packaging	tubes
Pack size	2 x 8 kg (16 kg)
Shelf life	min. 24 months
Color	beige
Consumption	approx. 1200 g/m ²
Working time	30 - 40 minutes*
Minimum application temperature	15 °C at ground level
Loadable	after approx. 12 hours*
Grindable	after approx. 24 hours*

*At 20 °C and 65% relative humidity.



EXTENDED APPLICATIONS:

- ▶ strip parquet
- ▶ solid wood flooring (15 - 22 mm)
- ▶ engineered wood flooring

SUBSTRATE PREPARATION:

The substrate must be sound, load-bearing, dry, free from cracks and free from materials (dirt, oil, grease) that would impair adhesion. Cement and calcium sulphate screeds must be abraded and vacuumed. Test the substrate in accordance with applicable standard or notices and report any deficiencies.

Any adhesion-reducing or unstable layers, e.g. release agents, loose adhesives, compounds, covering or paint residues, etc. must be removed, e.g. by brushing, abrading, grinding or shot-blasting. Thoroughly vacuum loose material and dust. Use a suitable primer from the UZIN Product Guide according to the type and condition of the substrate. Allow any primer that is applied to dry completely.

Priming is not necessary on standard, dry substrates suitable for wood flooring (cementitious or precast screeds). Calcium sulphate screeds, accelerated or rapid cementitious screeds, underfloor heating systems as well as special screed constructions have to be primed with UZIN PE 414 BiTurbo. Obtain application advice if in doubt.

The datasheets for other used products have to be observed.

APPLICATION:

1. Before use, allow the adhesive to come to room temperature. Fill UZIN ATD 100 with the tubes according to the instruction.
2. Apply an even coat of adhesive onto the substrate using UZIN ATD 100. Do not apply more adhesive than can be laid with good transfer onto the back of the wood flooring within the working time. Press down the wood flooring element well.
3. Apply an even coat of adhesive onto the substrate using a suitable notched trowel in areas, that are not accessible with UZIN ATD 100.
4. Remove residues while fresh with wipes from the UZIN Clean-Box. Hardened adhesive can only be removed mechanically.
5. Clean UZIN ATD 100 according to the instruction.

CONSUMPTION INFORMATION:

Parquet type	Toothings	Consumption approx.*
Multi-ply wood flooring / Strip parquet	B11	1000 - 1200 g/m ²
Solid wood flooring	Solid board notched trowel / B13	1200 g/m ²

*At 20 °C and 65% relative humidity, with tempered adhesive tubes.

IMPORTANT NOTES:

- ▶ A shelf life of 24 months when stored in moderately cool conditions, in the original packaging. Frost-resistant down to - 25 °C. Carefully and tightly reseal opened tubes and use the contents quickly. Allow tubes to come to room temperature before use.
- ▶ Best applied between 18 - 25 °C, with the floor temperature above 15 °C and relative air humidity below 65%. Low temperatures and low air humidity lengthen the working and drying time. Whilst high temperatures and high air humidity shorten the working and drying time.
- ▶ The substrate must be even when installing large-size elements. Observe the manufacturer specification if necessary.
- ▶ Minimum thickness of any levelling compound below the adhesive is 2 mm.
- ▶ Observe good drying of the levelling compound.
- ▶ The substructure of wooden floors must be dry. Adequate ventilation or rear-ventilation must be provided, e.g. by removing the existing expansion strip or by installing special skirtings with ventilation holes.
- ▶ Observe standard wood humidity.
- ▶ Observe adequate and uniform distance to rising components, depending on type of wood flooring and room size.
- ▶ Ready for grinding and surface treatment after 48 hours (suitable products on www.pallmann.net), with standard wood humidity, air humidity and sufficient acclimatised wood flooring.
- ▶ Follow the generally acknowledged rules of the trade and technology for the installation of wood flooring in respect of the applicable national standards (e.g. EN, DIN, OE, SIA, etc.)

SEALS OF QUALITY & ECOLABELS:

- ▶ Solvent-free, containing methoxysilane
- ▶ EMICODE EC 1 PLUS / Very low emission
- ▶ European Model EPD
- ▶ Suitable for sustainable building certifications according to: DGNB, QNG, BNB, BREEAM, LEED

COMPOSITION:

Silane-terminated prepolymers, mineral fillers, additives.

PROTECTION OF THE WORKPLACE AND THE ENVIRONMENT:

Solvent-free adhesive containing methoxysilane. Non flammable. Avoid contact with eyes and skin. When curing, produces traces of methanol. Ensure good ventilation during application. Wear protective gloves. After contact with skin wash with plenty of water and soap. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Observe safety information on product label as well as safety data sheet.

DISPOSAL:

Where possible, collect product residues and re-use. Do not allow dispersal into drains, sewers or ground. Empty,

scraped and drip-free containers are recyclable. Containers with liquid residue, as well as the liquid product, are classed as Special Waste. Dried product residues are classed as Construction Waste. Therefore collect waste material and allow to harden, then dispose as Construction Waste.